

PRODUCT DATA SHEET

APILON 33 T Series

PVC-NBR range recommended for extrusion and co-extrusion applications. Excellent nib-free finish for high-quality products and available in all colours. **4T 80-09/30** has a high nitrile content giving improved compression recovery characteristics and excellent migration resistance.

GRADE: **4T 80-09 / 30**

PROPERTY	TEST METHOD	DATA
Relative Density	DIN 53457	1.30
Hardness	DIN 53505 / ASTM D 2240	80° Shore A
Melt Flow Index 190 C / 49.05 N g/10min	ASTM D1238	10
Tear Strength (un-notched)	DIN 53515 / ASTM D624	60 KN/m
Tensile Strength	DIN 53504 / ASTM D 638	17.4 Mpa
Elongation at break	DIN 53504 / ASTM D 638	430 %

