

PRODUCT DATA SHEET

APILON 33 DP Series

PVC-NBR range recommended for extrusion and co-extrusion applications. Excellent nib-free finish for high-quality products and available in all colours. **DP 0176/70** is low-marring in contact with polycarbonate and has excellent U.V. stability.

GRADE: **DP 0176 / 70**

PROPERTY	TEST METHOD	DATA
Relative Density	DIN 53457	1.30
Hardness	DIN 53505 / ASTM D 2240	70° Shore A
Melt Flow Index 190 C / 49.05 N g/10min	ASTM D1238	3.5
Tear Strength (un-notched)	DIN 53515 / ASTM D624	28 KN/m
Tensile Strength	DIN 53504 / ASTM D 638	11.6 Mpa
Elongation at break	DIN 53504 / ASTM D 638	450 %

