

PRODUCT DATA SHEET

RAPLAN NL Series

SBS compounds with very good elastomeric properties suitable for both extrusion and moulding applications.

GRADE: **9210 NL**

PROPERTY	TEST METHOD	DATA
Relative Density	DIN 53457	0.90
Hardness	DIN 53505 / ASTM D 2240	25° Shore A
Melt Flow Index 190 C / 49.05 N g/10min	ASTM D1238	26
Tear Strength (un-notched)	DIN 53515 / ASTM D624	20 KN/m
Tensile Strength	DIN 53504 / ASTM D 638	5.4 Mpa
Elongation at break	DIN 53504 / ASTM D 638	1100 %

