

## PRODUCT DATA SHEET RAPLAN MB Series

SBS compounds with good elastomeric properties and excellent colourability. Designed specifically for injection moulding, but equally suitable for extrusion applications.

GRADE: **MB 55-65**

---

PROPERTY	TEST METHOD	DATA
<b>Relative Density</b>	DIN 53457	<b>1.0</b>
<b>Hardness</b>	DIN 53505 / ASTM D 2240	<b>55° Shore A</b>
<b>Melt Flow Index</b> 190 C / 49.05 N g/10min	ASTM D1238	<b>40</b>
<b>Tear Strength</b> ( un-notched )	DIN 53515 / ASTM D624	<b>23 KN/m</b>
<b>100% Modulus</b>	ASTM D638	<b>1.3 MPa</b>
<b>Tensile Strength</b>	DIN 53504 / ASTM D 638	<b>4.0 MPa</b>
<b>Elongation at break</b>	DIN 53504 / ASTM D 638	<b>600 %</b>
<b>Abrasion resistance</b>	DIN 53516	<b>250 mm3</b>

