

PRODUCT DATA SHEET

MEGOL T Series

Transparent SEBS-based compounds with excellent elastomeric properties, suitable for co-moulding and co-extrusion on to PP and PE.

T grades meet EEC decree 128/90 and all ingredients are covered by EEC synoptic document n6 CS/PM/2061, 2/4/93.

GRADE: **TA 60 P**

PROPERTY	TEST METHOD	DATA
Relative Density	DIN 53457	0.89
Hardness	DIN 53505 / ASTM D 2240	60° Shore A
Melt Flow Index 190 C / 49.05 N g/10min	ASTM D1238	150
Tear Strength (un-notched)	DIN 53515 / ASTM D624	36 KN/m
Tensile Strength	DIN 53504 / ASTM D 638	6.6 Mpa
Elongation at break	DIN 53504 / ASTM D 638	700 %

