

TORAY

# TORAY PLASTICS (MALAYSIA) SDN BERHAD (46619-P)

2628, MK. 1, SPT., Lorong Perusahaan 4, Prai Free Industrial Zone, 13600 Prai,  
Penang, Malaysia.

Tel. No : 04-3988088  
Fax. No: 04-3908975 (MD / Sales), 04-3974039 (Acct / Admin),  
04-3990563 (Purch), 04-3977357 (Material), 04-3997503 (Prod),  
04-3997502 (Eng), 04-3908977 (Tech)

## PROPERTIES OF TOYOLAC™ ASA (东丽ASA)

				ASA
Properties 物性	Test Method 试验法	Test Condition 试验条件	Unit 单位	TA50 X01
<b>Physical 物理性</b>				
Density 比重	ISO 1183	23°C	kg/m <sup>3</sup>	1060
<b>Rheology 流变性</b>				
Melt Flow Index 熔融指数	ISO 1133	220°C, 10kg	g/10min	43
<b>Mechanical 机械性</b>				
Tensile Strength 引张强度;降伏点	ISO 527	50 mm/min	MPa	42
Tensile Elongation 断裂伸长率	ISO 527	50 mm/min	%	> 10
Tensile Modulus 拉伸模量	ISO 527	1 mm/min	MPa	2000
Flexural Strength 弯曲强度	ISO 178	2 mm/min	MPa	64
Flexural Modulus 弯曲弹性模量	ISO 178	2 mm/min	MPa	2050
Charpy Impact Strength (Notched) 夏比缺口冲击强度	ISO 179/1eA	23°C/50%RH	kJ/m <sup>2</sup>	8
<b>Thermal 耐热性</b>				
Deflection Temperature Under Load 负载热变形温度	ISO 75	1.8MPa	°C	80
<b>Flammability 可燃性</b>				
Flammability 可燃性	UL 94	-	-	HB
<b>Appearance 外表</b>				
Glossiness 光泽度	Toray Method	Incident Angle 60°	%	96

Note: These values are typical values for this product under specific test conditions and not intended for use as limiting specification.

以上数据谨代表在特定条件下所得的测定值的代表例